

Stainless Steel Weld Process Selector Guide


COST PER POUND



SSSS Ś


Cost per pound is referencing commercial selling prices for each electrode type.

SPATTER LEVELS



Some processes, like SMAW, by nature have a tendency to produce more spatter than other processes such as GTAW welding or SAW.

Stainless Stick (SMAW) Stainless Solid Wire (GMAW) Stainless Cut Length (GTAW) Stainless Flux Cored (FCAW-G) Stainless Metal Cored (MCAW) Stainless Sub Arc (SAW)




EQUIPMENT COMPLEXITY

GTAW, MCAW and GMAW equipment that have pulse capability have more input variables and can be more complex than a process using a constant current (CC) or constant voltage (CV) power source.

SKILL LEVEL REQUIRED






The key to success in all welding joints is proper setup. However, some welding processes are more difficult to master than others. For this reason, GTAW requires the most skill.

BEAD APPEARANCE







Due to its high surface sheen, most stainless steel welds are required to blend well into the base material. GTAW accomplishes this, but is very slow. Conversely, a welder joining carbon to stainless steel may not be as concerned with the final bead appearance.

PRODUCTIVITY








The productivity scale is comparing the pounds per hour of weld metal deposited.


Stainless Stick (SMAW) Stainless Solid Wire (GMAW) Stainless Cut Length (GTAW) Stainless Flux Cored (FCAW-G) Stainless Metal Cored (MCAW) Stainless Sub Arc (SAW)



Processes relying on external shielding gas such as GTAW and GMAW are less suited for portable use than SMAW. While submerged arc welding could be implemented outdoors, the setup does not make it very portable.

Stainless Stick (SMAW) Stainless Solid Wire (GMAW) Stainless Cut Length (GTAW) Stainless Flux Cored (FCAW-G) Stainless Metal Cored (MCAW) Stainless Sub Arc (SAW)

PIPE WELDING PRODUCTIVITY



The 6G position requires all-position capable electrodes and will by nature have lower deposition rates. Roll pipe applications position the weld so that it is always in the flat position to maximize productivity and deposition rates.