

AWS E6013 (E4313*)

Hobart® 447C**DESCRIPTION:**

The versatility and the fast-freeze characteristics of the **Hobart 447C** makes it a favorite among welders, especially when the welding application shows signs of poor fit-up. It can be used with either AC or DC power sources, and also with low open-circuit voltage AC machines, providing a very stable arc and good bead appearance.

APPLICATIONS:

General purpose fabrication, machine parts, metal buildings and structures and shaft build-up.

FEATURES:

- Excellent arc stability
- Fast-freeze
- All-position
- Slag removes easily
- Softer arc than Hobart 447A

BENEFITS:

- Welding accuracy and efficiency
- Excellent for poor fit-up
- Welds in flat, horizontal, vertical, and overhead position
- Quick clean-up
- Easier to control, less spatter

TYPICAL WELD METAL PROPERTIES(Chem Pad):**

Weld Metal Analysis		AWS Spec (max)
Carbon (C)	0.10	not required
Manganese (Mn)	0.48	not required
Phosphorus (P)	0.019	not required
Sulphur (S)	0.022	not required
Silicon (Si)	0.35	not required

TYPICAL MECHANICAL PROPERTIES(AW):**

		AWS Spec (min)
Tensile Strength	70,000 psi (483 MPa)	60,000 psi
Yield Strength	65,000 psi (448 MPa)	48,000 psi
Elongation % in 2"	20% to 28%	17%
Reduction of Area	25% to 55%	not required

TYPICAL CHARPY-V-NOTCH IMPACT VALUES(AW):**

Not applicable

TYPE OF CURRENT: AC, DCEN or DCEP

CONFORMANCES AND APPROVALS:

- AWS A5.1, E6013, ASME SFA 5.1, F-2, A-1
- ABS E6013
- CWB E4313

* Metric AWS classification

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers Company expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with AWS A5.1 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers Company.

Hobart Brothers Company • 400 Trade Square East • Troy, OH 45373
PH: (800) 424-1543 • FX: 800-541-6607 • www.hobartbrothers.com



RECOMMENDED WELDING PROCEDURES:

GENERAL:	AC; electrode negative, work positive (DCEN); or electrode positive, work negative (DCEP)
ARC LENGTH:	Average length (1/8" to 1/4")
FLAT:	Angle electrodes 10-15° from 90° with higher heat than E6011 electrodes
VERTICAL-UP:	Reduce amperage from flat position
VERTICAL-DOWN:	Use higher amperage and faster travel staying ahead of puddle
OVERHEAD:	Use slight whipping motion; multi-pass for build-up
STORAGE:	60°F to 100°F, (20° to 40°C) and below 50% relative humidity or holding oven @ 100° to 120°F (38° to 49°C)
RECONDITIONING:	250°F to 300°F, (121° to 149°C) for one hour @ temperature

RECOMMENDED OPERATING PARAMETERS:

Diameter		Type of Power	Minimum Amps	Optimum* Amps	Maximum Amps
Inches	mm				
3/32	2.4	AC, DCEN or DCEP	40	70	80
1/8	3.2	AC, DCEN or DCEP	70	100	120
5/32	4.0	AC, DCEN or DCEP	130	150	160

*For out-of-position welding, reduce amperage shown by 15%.

TYPICAL DEPOSITION DATA (at optimum):

Diameter		Type of Power	Amps	Volts	Deposition Rate lbs/hr	Deposition Efficiency*%
Inches	mm					
3/32	2.4	AC	70	19 - 26.5	1.35	63.7
1/8	3.2	AC	100	18.5 - 22.5	1.85	66.1
5/32	4.0	AC	150	20 - 24	2.67	61.6

*Allowance made for 2" stub loss included.

AVAILABLE DIAMETERS AND PACKAGES:

Diameter		Length		50-Lb. Carton
Inches	mm	Inches	mm	
3/32	2.4	14"	355	S117132-031
1/8	3.2	14"	355	S117144-031
5/32	4.0	14"	355	S117151-031

Material Safety Data Sheets on any Hobart Brothers Company product may be obtained from Hobart Customer Service.

Because Hobart Brothers Company is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.

Hobart is a registered trademark of Hobart Brothers Company, Troy, Ohio

