



# METALLOY<sup>®</sup> 76

**GAS-SHIELDED METAL-CORED WIRE**  
AWS E70C-6M H4  
EN758, T46 4 M M 2 H5

100621 (replaces 100427)

**Metalloy 76** has higher manganese and silicon levels than Metalloy 71 with slightly lower spatter and higher strength. The increased deoxidization level allows for more tolerance of mill scale, with fewer root pores than Metalloy 71. Metalloy 76 is recommended for single-pass and multi-pass welding in flat and horizontal positions with 75-95% Ar/CO<sub>2</sub>. The wetting action is better than solid wire, minimizing cold lap on heavier sections of steel.

### PRODUCT CHARACTERISTICS:

- Higher deoxidizer levels for improved performance on mill scaled plate
- Better wetting action than solid wire minimizes cold lap
- Superb operator appeal
- Good choice to use for short-circuit or pulse applications.

### SPECIFICATIONS:

E70C-6M H4 per AWS A5.18, ASME SFA 5.18  
Lloyd's Register of Shipping Grade 3Y40S H15  
DNV Grade III Y40MS  
Bureau Veritas S3YM

CWB E491C-6M H4  
ABS Grade 3SA, 3YSA  
EN758, T46 4 M M 2 H5

### SHIELDING GAS:

75-95% Ar/Bal CO<sub>2</sub>, 35-50 cfh

### WELDING POSITIONS:

CV Spray - flat, horizontal, vertical down  
Pulse and short arc - all positions

### STANDARD DIAMETERS:

.035", .045", .052", 1/16", 5/64"

### WELD TEST PARAMETERS:

Metalloy 76 1/16" diameter electrode was welded using 75% Ar/25% CO<sub>2</sub> shielding gas with flow rate of 50 cfh, 350 amps (325 ipm), DCEP, and 30 volts, with 3/4" electrical stick-out and 300°±25°F interpass temperature. A total of six layers were welded, two passes for each Layers 1 through 6. The direction of travel was reversed for each layer.

### TYPICAL UNDILUTED WELD METAL CHEMISTRY:

	C	Mn	Si	P	S
75% Ar/25% CO <sub>2</sub>	0.05	1.58	0.71	0.012	0.013
90% Ar/10% CO <sub>2</sub>	0.05	1.69	0.78	0.012	0.013

**TYPICAL DIFFUSIBLE HYDROGEN:** 2.10 ml/100gr (75% Ar/25% CO<sub>2</sub>)  
2.15 ml/100gr (90% Ar/10% CO<sub>2</sub>)

<b>TYPICAL MECHANICAL PROPERTIES:</b>	<b>75% Ar/25% CO<sub>2</sub></b>	<b>90% Ar/10% CO<sub>2</sub></b>
Tensile Strength	88,700 psi (612 MPa)	92,500 psi (638 MPa)
Yield Strength	78,200 psi (539 MPa)	82,600 psi (570 MPa)
Elongation	27%	26%
CVN @ 0°F (-18°C)	72 ft•lbs.(98 J)	68 ft•lbs.(92 J)
CVN @ -20°F (-29°C)	53 ft•lbs.(72J)	46 ft•lbs.(62 J)
CVN @ -40°F (-40°C)	34 ft•lbs. (46J)	

\*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers Company expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS A5.18 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers Company.

www.hobartbrothers.com  
400 Trade Square East  
Troy, OH 45373  
PH: 1-800-424-1543  
FX: 1-800-541-6607



# METALLOY<sup>®</sup>76

GAS-SHIELDED METAL-CORED WIRE  
 AWS E70C-6M H4  
 EN758, T46 4 MM 2 H5

## RECOMMENDED OPERATING PARAMETERS:

The information below was determined by welding performed with 75% Ar/25% CO<sub>2</sub> shielding gas at a flow rate of 35 to 50 cubic feet per hour.

Diameter, Electrical Stickout (ES) Position	Arc Voltage (volts)	Current DCEP (+) (amps)	Approx. Wire Feed Speed (in/min)	Deposition Rate (lbs/hr)
.035" 1/2 ± 1/8" Flat and Horizontal	26	200	550	8.47
	<b>28</b>	<b>250</b>	<b>760</b>	<b>11.97</b>
	30	260	791	12.54
.045" 5/8" ± 1/8" Flat and Horizontal	27	200	273	6.11
	29	250	395	9.42
	<b>31</b>	<b>300</b>	<b>520</b>	<b>13.0</b>
.052" 5/8" ± 1/8" Flat and Horizontal	30	250	265	7.95
	30	300	355	11.64
	<b>32</b>	<b>350</b>	<b>450</b>	<b>15.11</b>
1/16" 3/4" ± 1/4" Flat and Horizontal	34	400	640	16.51
	30	275	185	7.66
	30	300	220	9.66
	<b>31</b>	<b>350</b>	<b>270</b>	<b>12.44</b>
	32	400	330	15.75
	36	450	381	18.21

**Bold:** Optimum parameters for welder appeal.

### Notice:

Actual use of the product may produce varying results due to conditions and welding techniques over which Tri-Mark has no control, including, but not limited to, plate chemistry, weldment design, fabrication methods, electrode size, welding procedure, service requirements and environment. The purchaser is solely responsible for determining the suitability of Tri-Mark products for the purchaser's own use. Any prior representations shall not be binding. Tri-Mark disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

### Caution:

Consumers should be thoroughly familiar with the safety precautions shown on the Warning Label posted on each shipment in and in American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 550 NW Le-Jeune Road, Miami, FL 33126, and OSHA Safety and Health Standards 29 CFR 1910, available from the U.S. Department of Labor, Washington, D.C. 20210.