



TM-770

GAS-SHIELDED FLUX-CORED WIRE
AWS E71T-1M, E71T-12MJ H8
EN758, T 42 2 P M 2 H10

070725 (replaces 070227)

TM-770 combines superior welding performance with outstanding mechanical properties. TM-770 has exceptional operator appeal for a wire with such superb physical properties, an arc that is soft and stable, and low fume levels with virtually no spatter. Even in the vertical-up position, the welds produced with TM-770 will have a flat bead profile. This wire is designed for both single and multiple-pass welding in all positions, using a shielding gas of 75-85% Ar/15-25% CO₂. Typical applications include shipbuilding, offshore structures, and general fabrication where high impact properties, ease of operation and high productivity are required.

PRODUCT CHARACTERISTICS:

- Low fume levels with virtually no spatter.
- Good CVN toughness at sub-zero temperatures.
- Meets MIL specifications for mechanical properties and diffusible hydrogen levels.
- NOT TO BE USED WITH 100% CO₂.

SPECIFICATIONS:

E71T-1M, E71T-12MJ H8 per AWS A5.20, ASME SFA 5.20
 ABS Grade 3SA, 3YSA
 Bureau Veritas S3YM
 CWB 75% Ar/25% CO₂; 85% Ar/15% CO₂ E491T-12M H8
 DNV Grade III Y40MS
 Germanischer Lloyd 3Y40H10S
 Lloyd's Register of Shipping, Grade 3S, 3YS H15
 Military Spec MIL-E-24403/1 Class MIL-71T-1M, MIL-71T-1-HYM
 EN758, T 42 2 P M 2 H10

SHIELDING GAS:

75-85% Ar/Bal CO₂, 35-50 cfh

WELDING POSITIONS:

All positions

STANDARD DIAMETERS:

.035", .045", .052", 1/16"

WELD TEST PARAMETERS:

TM-770 1/16" diameter electrode was welded using 80% Ar/20%CO₂ shielding gas with flow rate of 40 cfh, 275 amps (241 ipm), DCEP, and 26 volts with 3/4" electric stick-out and 300± 25°F interpass temperature. A total of six layers were welded, two passes each for Layers 1 through 6. The direction of travel was reversed for each layer.

TYPICAL UNDILUTED WELD METAL CHEMISTRY*:

	C	Mn	Si	P	S	Ni
80% Ar/20% CO ₂	0.03	1.14	0.29	0.009	0.003	0.34

TYPICAL MECHANICAL PROPERTIES*:

Tensile Strength 81,000 psi (560 MPa)
 Yield Strength 77,000 psi (528 MPa)
 Elongation 27%
 CVN @ 0°F (-18°C) 176 ft•lbs (239 J)
 CVN @ -40°F (-40°C) 131 ft•lbs (178 J)

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers Company expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS A5.20 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers Company.

www.hobartbrothers.com
 400 Trade Square East
 Troy, OH 45373
 PH: 1-800-424-1543
 FX: 1-800-541-6607



TM-770

**GAS-SHIELDED FLUX-CORED WIRE
AWS E71T-1M, E71T-12MJ H8**

RECOMMENDED OPERATING PARAMETERS:

The information below was determined by welding performed with 75 Ar/25% CO₂ shielding gas at a flow rate of 35 cfh.

Diameter, Electrical Stickout (ES) Position	Arc Voltage (volts)	Current DCEP (+) (amps)	Approx. Wire Feed Speed (in/min)	Deposition Rate (lbs/hr)
.045" 1/2 to 3/4" Flat and Horizontal	24	100	220	4.6
	31	275	630	to
	33	300	730	15.4
Vertical	24	150	220	4.6
	26	190	335	to
	27	220	430	8.4
Overhead	24	150	220	4.8
	26	200	370	to
	29	250	530	10.3
.052" 1/2" to 3/4" Flat and Horizontal	23	150	160	4.2
	29	300	435	to
	35	350	585	15.0
Vertical	24	150	160	4.2
	26	200	225	to
	28	250	320	8.4
Overhead	24	150	160	4.2
	27	225	290	to
	28	250	320	8.4
1/16" 1/2" to 3/4" Flat and Horizontal	24	200	180	6.3
	27	350	410	to
	28	450	580	22.6
Vertical	24	200	180	6.3
	25	220	210	to
	27	275	290	10.4
Overhead	26	200	180	6.3
	27	250	210	to
	28	275	290	10.4

Bold: Optimum parameters for welder appeal.

Notice:

Actual use of the product may produce varying results due to conditions and welding techniques over which Tri-Mark has no control, including, but not limited to, plate chemistry, weldment design, fabrication methods, electrode size, welding procedure, service requirements and environment. The purchaser is solely responsible for determining the suitability of Tri-Mark products for the purchaser's own use. Any prior representations shall not be binding. Tri-Mark disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

Caution:

Consumers should be thoroughly familiar with the safety precautions shown on the Warning Label posted on each shipment in and in American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 550 NW LeJeune Road, Miami, FL 33126, and OSHA Safety and Health Standards 29 CFR 1910, available from the U.S. Department of Labor, Washington, D.C. 20210.