

Certificate of Conformance to Requirements for Welding Electrode

Product Type: FabCOR 702 1/16 60 CL

Classification: E70C-3C

Specifications: AWS A5.18-01; ASME SFA5.18

Diameter Tested: 1/16"

 Date Tested:
 3/17/2016

 Date Generated:
 3/21/2016

This is to certify that the product named above and supplied on the referenced order number is of the same classification, manufacturing process, and material requirements as the material which was used for the test that was concluded on the date shown, the results of which are shown below. All tests required by the specifications shown for classification were performed at that time and the material tested met all requirements. It was manufactured and supplied by the Quality System Program of Hobart Brothers, which meets the requirements of ISO 9001, ANSI/AWS A5.01, and other specification and Military requirements, as applicable. This document supplies actual test results of non-specific inspection in conformance with the requirements of EN 10204, type 2.2 certification.

THE STEEL USED IN THIS LOT OF MATERIAL WAS MELTED AND MANUFACTURED IN THE U.S.A.

Test Settings																							
Shielding Medium		Amps / Polarity	Volts			WFS in/min(m/min)		ESO in	ı(mm)		Preheat F(C)			În	Interpass F(C)			Travel Speed in/min(cm/min)					
SG-C 100°	SG-C 100%CO2		P	32	32 270 (6		.9)		3/4 (19)	Room Te			np 300(14			49)	9)			12 (30.5)		
Mechanical Properties - Tensile																							
Shielding	Shielding Medium			Test	Testing Conditions			Ult. Tensile Strength ps (MPa)				Yield Strength psi (MPa)			Elc	Elong.% in 2"			
SG-C 100%CO2		PD0899		Aged 48 Hrs 220F			86,000 (594)					73,000 (502)				28							
Mechanical Properties - Impact																							
Shielding N	Shielding Medium		Ref. No. Tes		ondition	s T	emp. I	F (C)		Individu	i.lb.(J)			Avg. ft.lb.(J)			J) Type						
SG-C 100	SG-C 100%CO2		PD0899		As Welded			0 (-18)			,65,65 (92,88,88)				66 (89			9) Charpy-V-Notc				.ch	
Ref.No.	Ref.No. Radiographic Inspection					Fillet Weld Test																	
PD0899	PD0899 Conforms				H	Iorizonta	d :					Overhead:							Vertical:				
							hem	ical A	nalys	is													
Shielding	Shielding Medium / Ref. No		С	Mn	Р	S	Si	Cu	Cr	V	Ni	Мо	AI	TiN	lb (Co B	3 W	Sn I	e S	b N	Mg	Zn	Be
SG-C 100%CO2 / CD10775			80.0	1.35	0.006	0.023	0.63	0.03	0.06	< .01	0.02	0.02											

land A. Thomaso

Dave Thomas, Quality Assurance Rep.

Certification and Limited Warranty - Data for the above supplied product are those obtained when welded and tested in accordance with the above specification. All tests for the above classification were satisfied. Other tests and procedures may produce different results. Hobart Brothers produces welding consumables under continuing quality assurance programs audited and approved by the American Bureau of Shipping ("ABS").