

## **Certificate of Conformance** to Requirements for Welding Electrode

Hobart

Product Type: QCL-3 ER70S-3 Classification:

A5.18/SFA 5.18, F-6, A-1 Specifications:

.045 Diameter Tested:

Date Tested: 8/24/2015 Date Generated: 12/15/2016

This is to certify that the product named above and supplied on the referenced order number is of the same classification, manufacturing process, and material requirements as the material which was used for the test that was concluded on the date shown, the results of which are shown below. All tests required by the specifications shown for classification were performed at that time and the material tested met all requirements. It was manufactured and supplied by the Quality System Program of Hobart Brothers, which meets the requirements of ISO9001, ANSI/AWS A5.01, and other specification and Military requirements, as applicable. This document supplies actual test results of non-specific inspection in conformance with the requirements of EN 10204, type 2.2 certification.

**Test Settings** 

Shielding Medium	Amps / Polarity	Volts WFS in/min	(m/min)	ESO in(mm)	Preheat F(C)	Interpass F(C)	Travel Speed in/min(cm/min)							
SG-C 100%CO2	285 / DCEP	31 47	0 (11.9)	9) 3/4 (19) Room Ten		300(149)	10 (25.4)							
Mechanical Properties - Tensile														
Shielding Medium	Ref. No.	Testing Conditions		llt. Tensile Strength լ (MPa)	psi Yield Strengt	h psi (MPa)	Elong.% in 2"							
SG-C 100%CO2	PC7197	As Welded		80,000 ( 553 )	65,000	( 450 )	25							
Mechanical Properties - Impact														
Shielding Medium	Ref. No.	Testing Conditions	Temp. F	(C) Individ	duals ft.lb.(J)	Avg. ft.lb.(J)	Туре							
CC C 1000/ CO2	DC7107	A a Maldad		4 ( 20) 91	20) 91 91 60 (110 110 04) 77 ( 104 )		Charny V/ Notah							

Shielding	Shielding Medium Ref. No.		Testing Conditions	Temp. F (C)	Individuals ft.lb.(J)	Avg. ft.lb.(J)	Type					
SG-C 10	SG-C 100%CO2 PC7197		As Welded	-4 (-20)	81,81,69 (110,110,94)	77 ( 104 )	Charpy-V-Notch					
Ref.No. Radiographic Inspection					Fillet Weld Test							
PC7197 None			Horizon	tal:	Overhead:		Vertical:					
Chemical Analysis												

	Shielding Medium / Ref. No	С	Mn	Р	S	Si	Cu	Cr	V	Ni	Мо	AI	Ti	Nb	Со	В	W	Sn	Fe	Sb	N	Mg	Zn	Be
H	NONE / CD01572	0.09	1.20	0.012	0.010	0.64	0.09	0.04	0.00	0.04	0.01	Ш	П		'	Г			'	' '	Ш			

Dave Thomas, Quality Assurance Rep.

Certification and Limited Warranty - Data for the above supplied product are those obtained when welded and tested in accordance with the above specification. All tests for the above classification were satisfied. Other tests and procedures may produce different results. Hobart Brothers produces welding consumables under continuing quality assurance programs audited and approved by the American Bureau of Shipping ("ABS").