



Certificate of Conformance to Requirements for Welding Electrode

Product Type: TM-121
 Classification: E71T-11
 Specifications: AWS A5.20; ASME SFA5.20
 Diameter Tested: .035"; 3/32"
 Date Tested: 08/27/2013
 Date Generated: 5/7/2014

This is to certify that the product named above and supplied on the referenced order number is of the same classification, manufacturing process, and material requirements as the material which was used for the test that was concluded on the date shown, the results of which are shown below. All tests required by the specifications shown for classification were performed at that time and the material tested met all requirements. It was manufactured and supplied by the Quality System Program of Hobart Brothers, which meets the requirements of ISO9001, ANSI/AWS A5.01, and other specification and Military requirements, as applicable. This document supplies actual test results of non-specific inspection in conformance with the requirements of EN 10204, type 2.2 certification.

Test Settings

| Shielding Medium | Amps / Polarity | Volts | WFS in/min(m/min) | ESO in(mm) | Preheat F(C) | Interpass F(C) | Travel Speed in/min(cm/min) |
|------------------|-----------------|-------|----------------------|------------|--------------|----------------|--------------------------------|
| SELF SHIELDING | 260 / DCEN | 20 | 50 (1.3) | 3/4 (19) | 70(21) | 300(149) | 7 (17.8) |
| SELF SHIELDING | 200 / DCEN | 20 | 390 (9.9) | 1/2 (13) | 70(21) | 325(163) | 9 (22.9) |

Mechanical Properties - Tensile

| Shielding Medium | Ref. No. | Testing Conditions | Ult. Tensile Strength psi (MPa) | Yield Strength psi (MPa) | Elong.% in 2" |
|------------------|----------|--------------------|------------------------------------|--------------------------|---------------|
| SELF SHIELDING | PB9996 | Aged 48 Hrs 200F | 89,000 (614) | 64,000 (439) | 22 |
| SELF SHIELDING | PC0986 | Aged 48 Hrs 200F | 90,000 (621) | 60,000 (414) | 25 |

| Ref.No. | Radiographic Inspection | Fillet Weld Test | | | |
|---------|-------------------------|------------------|------------|------------|----------|
| PB9996 | Conforms | Horizontal : | Overhead : | Vertical : | |
| PC0986 | Conforms | Horizontal : | Overhead : | Vertical : | Conforms |

Chemical Analysis

| Shielding Medium / Ref. No | C | Mn | P | S | Si | Cu | Cr | V | Ni | Mo | Al | Ti | Nb | Co | B | W | Sn | Fe | Sb | N | Mg | Zn | Be |
|----------------------------|------|------|-------|-------|------|------|------|-------|------|------|------|----|----|----|---|---|----|----|----|---|----|----|----|
| SELF SHIELDING / CB60023 | 0.28 | 0.32 | 0.007 | 0.004 | 0.10 | 0.04 | 0.04 | < .01 | 0.02 | 0.01 | 1.18 | | | | | | | | | | | | |
| SELF SHIELDING / CB61819 | 0.22 | 0.32 | 0.010 | 0.003 | 0.15 | 0.02 | 0.02 | < .01 | 0.01 | 0.01 | 1.49 | | | | | | | | | | | | |

J. H. O'Leary

Joe O'Leary, Quality Assurance Rep.

Certification and Limited Warranty - Data for the above supplied product are those obtained when welded and tested in accordance with the above specification. All tests for the above classification were satisfied. Other tests and procedures may produce different results. Hobart Brothers produces welding consumables under continuing quality assurance programs audited and approved by the American Bureau of Shipping ("ABS").