


Hobart® Maxal® 4047



AWS A5.10: ER4047, R4047

WELDING POSITIONS:



FEATURES:

- Low melting temperature/high fluidity
- Excellent wetting action for joint sealing applications
- Low welding smut and discoloration
- Very low ductility, formability, and toughness
- Moderate electrical conductivity and thermal conductivity

BENEFITS:

- Excellent corrosion resistance
- Very lowest shrinkage rate/reduced distortion
- Low hot cracking sensitivity in most applications

APPLICATIONS:

- Welding 6xxx alloys
- Radiators and air conditioning components
- General repair and maintenance
- Water and gas tight applications

SHIELDING GAS: 100% Argon (Ar) or Argon/Helium mixtures, typical: GMAW - 35-50 cfh (14-24 l/min), GTAW 20-30 cfh (10-14 l/min).

TYPE OF CURRENT: Direct Current Electrode Positive (DCEP) for GMAW, AC for GTAW

STANDARD DIAMETERS: 0.035" (0.9 mm), 3/64" (1.2 mm),

STORAGE: Product should be stored in a dry, enclosed environment, and in its original intact packaging

TYPICAL CHEMICAL VALUES*:

Weld Metal Analysis (%)	ER & R 4047
Silicon (Si)	11.0-13.0
Iron (Fe)	0.8
Copper (Cu)	0.30
Manganese (Mn)	0.15
Magnesium (Mg)	0.00
Zinc (Zn)	0.10
Titanium (Ti)	—
Beryllium (Be)	<0.0003
Others Each	0.05
Others Total	0.15
Aluminum (Al)	Remainder

*Unless noted-single values are maximums.

TYPICAL PROPERTIES:

Melting Range	Density	Electrical/Thermal Conductivity
1070-1080°F	0.096 lbs/in ³	40% IACS/1040 EU

As Welded UTS Typical	Anodized Color	Elevated Temp. Applications +150°F
38 ksi	Dark Gray	YES

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers LLC expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with AWS A5.10 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers LLC.

Hobart® Maxal® 4047

Diameter		Base Material Thickness		Amps		Volts		Wire-Feed Speed (ipm)	
Inches	(mm)	Inches	(mm)	4xxx	5xxx	4xxx	5xxx	4xxx	5xxx
0.035	(0.9)	1/16	(1.6)	90	100	23	21	300	350
0.035	(0.9)	1/8	(3.2)	130	140	24	22	400	450
3/64	(1.2)	3/32	(2.4)	110	120	25	24	170	220
3/64	(1.2)	1/8	(3.2)	150	160	26	25	270	330
3/64	(1.2)	1/4	(6.4)	190	220	26	25	320	370
3/64	(1.2)	3/8	(9.5)	220	230	27	25	390	450

Maintaining a proper welding procedure - including pre-heat and interpass temperatures - may be critical depending on the type and thickness of aluminum being welded.

See Above: This information was determined by welding using 100%Argon shielding gas with a flow rate between 35-50 cfh (14-24 l/min).

AVAILABLE DIAMETERS AND PACKAGES: For a complete list of diameters and packaging, please contact Hobart Brothers at (800) 424-1543 or (937) 332-5188 for International Customer Service.

Diameter Inches (mm)	16-lb. (7.3 kg) Wire Basket	300-lb. (136 kg) Drum
Net Pallet Weight	1296-lb (588 kg)	600-lb. (272 kg)
0.035 (0.9)	404703512	—
3/64 (1.2)	404704712	404704723

300 lb drum dimensions: diameter = 23-1/2"; height = 36"

CONFORMANCES AND APPROVALS:

- AWS A5.10, ER4047, R4047
- ASME SFA 5.10, ER4047, R4047
- AWS A5.01 Class S1, Schedule F
- vd TUV 1153

TECHNICAL QUESTIONS? For technical support of Hobart Filler Metals products, contact the Applications Engineering department by phone toll-free at 1-800-532-2618 or by e-mail at Applications.Engineering@hobartbrothers.com

CAUTION:

Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36th St., Miami, FL 33166 (can also be downloaded online at www.aws.org); OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210

Safety Data Sheets on any Hobart Brothers LLC product may be obtained from Hobart Customer Service or at www.hobartbrothers.com.

Because Hobart Brothers LLC is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.

Hobart is a registered trademark of Hobart Brothers LLC, Troy, Ohio.

Revision Date: 210805 (Replaces 210729)

624-C, INDEX

