



CERTIFICATE OF ANALYSIS

CUSTOMER :
MARKED FOR :
PACK SLIP\ORDER# :

P.O. NUMBER : 118937
DATE : 11/21/2017
WORK ORDER :

TYPE : 308/308L

SIZE : 1/8"*36"

LOT NO. : 7092575007

LBS SHIPPED : 10 lbs

HEAT NO. : E87750

SPECIFICATION : AWS A5.9, ASME SFA5.9
ER308/ER308L

PART NUMBER : S512546-112

Actual Chemistry :

FILLER METAL CHEMISTRY(%)

| | |
|----|-------|
| C | 0.018 |
| Cr | 19.75 |
| NI | 10.36 |
| Mo | 0.13 |
| Mn | 1.54 |
| Si | 0.50 |
| P | 0.023 |
| S | 0.018 |
| Cu | 0.11 |
| Nb | 0.011 |
| N | 0.040 |

This material has not come in contact with mercury or mercury containing compounds.

Typical Mechanical Properties :

85,000 Tensile Psi
58,000 Yield Psi
36 % Elongation
Charpy V-Notch Average = 43 Ft Lbs. @ -320 Degrees F

Ferrite(s) :

FN (Magnetic)
10.0 FN (DeLong)
9.1 FN (WRC)
8.7 % Ferrite (Schaeffler)

This typical mechanical information should not be construed as actual results.

We hereby certify that the above product has been classified in accordance with the listed specification and conforms to all applicable requirements thereof.

Filler Metals Quality Assurance

Hobart Brothers Company

Hobart Square

Troy, Ohio 45373

Authorized Signature

J. M. Wark