



WELDING PRODUCTS

CERTIFICATE OF ANALYSIS

CUSTOMER :
MARKED FOR :
PACK SLIP/ORDER# :

P.O. NUMBER : 119697
DATE : 04/29/2021
WORK ORDER :

TYPE : 316/316L

SIZE : 1/16" x 3/16"

LOT NO. : 210325824T16

LBS SHIPPED : 10 lbs

HEAT NO. : E37824

SPECIFICATION : AWS A5.9, ASME SFA-5.9

PART NUMBER : S512311-112

ER316/ER316L EN 10204 3.1 (For Actual Chemistry Only)

Actual Chemistry :

FILLER METAL CHEMISTRY(%)

C	0.011
Cr	18.00
Ni	12.18
Mo	2.50
Mn	1.50
Si	0.56
P	0.027
S	0.001
Cu	0.32
Nb	0.018
N	0.040

This material has not come in contact with mercury or mercury containing compounds.

Typical Mechanical Properties :

86,000 Tensile Psi
57,000 Yield Psi
36 % Elongation

Charpy V-Notch Average = 34 Ft Lbs. @ -320 Degrees F

This typical mechanical information should not be construed as actual results.

Ferrite(s) :

FN (Magnetic)
8.0 FN (DeLong)
5.9 FN (WRC)
6.5 % Ferrite (Schaeffler)

We hereby certify that the above product has been classified in accordance with the listed specification and conforms to all applicable requirements thereof.

Filler Metals Quality Assurance

Hobart Brothers Company

Hobart Square

Troy, Ohio 45373

Authorized Signature