



**Certificate of Conformance
to Requirements for Welding Electrode**

Product Type: **FabCO 991K2**
 Classification: **E91T1-K2C H8; E91T1-K2M H8**
 Specifications: **AWS A5.29/A5.29M; ASME SFA 5.29**
 Diameter Tested: **.045"**
 Date Tested: **8/03/2023**
 Date Generated: **8/16/2023**

This is to certify that the product named above and supplied on the referenced order number is of the same classification, manufacturing process, and material requirements as the material which was used for the test that was concluded on the date shown, the results of which are shown below. All tests required by the specifications shown for classification were performed at that time and the material tested met all requirements. It was manufactured and supplied by the Quality System Program of Hobart Brothers, which meets the requirements of ISO 9001, ANSI/AWS A5.01, and other specification and Military requirements, as applicable. This document supplies actual test results of non-specific inspection in conformance with the requirements of EN 10204, type 2.2 certification.

THE STEEL USED IN THIS LOT OF MATERIAL WAS MELTED AND MANUFACTURED IN THE U.S.A.

Test Settings

Shielding Medium	Amps / Polarity	Volts	WFS in/min(m/min)	ESO in(mm)	Preheat F(C)	Interpass F(C)	Travel Speed in/min(cm/min)
C1	225 / DCEP	24	410 (10.4)	3/4 (19)	300(149)	300(149)	12.5 (31.8)
M21-ArC-25	225 / DCEP	24	400 (10.2)	5/8 (16)	300(149)	300(149)	12.5 (31.8)

Mechanical Properties - Tensile

Shielding Medium	Ref. No.	Testing Conditions	Ult. Tensile Strength psi (MPa)	Yield Strength psi (MPa)	Elong.% in 2"
C1	PE6653	Aged 48 Hrs 220F	93,000 (640)	88,000 (606)	22
M21-ArC-25	PE6654	Aged 48 Hrs 220F	102,000 (703)	96,000 (663)	20

Mechanical Properties - Impact

Shielding Medium	Ref. No.	Testing Conditions	Temp. F (C)	Individuals ft.lb.(J)	Avg. ft.lb.(J)	Type
C1	PE6653	As Welded	0 (-18)	77,87,77 (104,118,104)	80 (109)	Charpy-V-Notch
M21-ArC-25	PE6654	As Welded	0 (-18)	64,62,63 (87,84,85)	63 (85)	Charpy-V-Notch

Ref.No.	Radiographic Inspection	Fillet Weld Test			
		Horizontal :	Overhead :	Vertical :	Conforms
PE6653	Conforms	Horizontal :	Overhead :	Vertical :	Conforms
PE6654	Conforms	Horizontal :	Overhead :	Vertical :	Conforms

Chemical Analysis

Shielding Medium / Ref. No	C	Mn	P	S	Si	Cu	Cr	V	Ni	Mo	Al	Ti	Nb	Co	B	W	Sn	Fe	Sb	N	Mg	Zn	Be	Sb	As
C1 / CD97655	0.05	0.99	0.012	0.011	0.26	0.03	0.03	0.02	1.56	0.01					0.0064										
M21-ArC-25 / CD97801	0.06	1.22	0.012	0.010	0.32	0.03	0.04	0.02	1.66	0.01					0.0073										

Diffusible Hydrogen Collected per AWS A4.3

C1	3.5 ml/100g of weld metal for .045 in diameter 27% relative humidity
M21-ArC-25	3.9 ml/100g of weld metal for .045 in diameter 27% relative humidity

James A. Owens

James A. Owens, Q.A. Specialist

Certification and Limited Warranty - Data for the above supplied product are those obtained when welded and tested in accordance with the above specification. All tests for the above classification were satisfied. Other tests and procedures may produce different results.