

Certificate of Conformance to Requirements for Welding Electrode

Product Type: FabCO Hornet

Classification: E71T-1C,E71T-1M,E71T-9C,E71T-9M H8
Specifications: AWS A5.20/A5.20M; ASME SFA 5.20

Diameter Tested: 1/16"

Date Tested: **7/14/2020**Date Generated: **7/21/2020**

This is to certify that the product named above and supplied on the referenced order number is of the same classification, manufacturing process, and material requirements as the material which was used for the test that was concluded on the date shown, the results of which are shown below. All tests required by the specifications shown for classification were performed at that time and the material tested met all requirements. It was manufactured and supplied by the Quality System Program of Hobart Brothers, which meets the requirements of ISO 9001, ANSI/AWS A5.01, and other specification and Military requirements, as applicable. This document supplies actual test results of non-specific inspection in conformance with the requirements of EN 10204, type 2.2 certification.

THE STEEL USED IN THIS LOT OF MATERIAL WAS MELTED AND MANUFACTURED IN THE U.S.A.

Test Settings

Shielding Medium	Amps / Polarity	Volts	WFS in/min(m/min)	ESO in(mm)	Preheat F(C)	Interpass F(C)	Travel Speed in/min(cm/min)				
M21-ArC-25	275 / DCEP	27	240 (6.1)	3/4 (19)	Room Temp	300(149)	10 (25.4)				
C1 (100% CO2)	275 / DCEP	27	240 (6.1)	3/4 (19)	Room Temp	300(149)	10 (25.4)				

Mechanical Properties - Tensile

Shielding Medium	Ref. No.	Testing Conditions	Ult. Tensile Strength psi (MPa)	Yield Strength psi (MPa)	Elong.% in 2"
M21-ArC-25	PD9829	Aged 48 Hrs 220F	84,000 (581)	75,000 (519)	28
C1 (100% CO2)	PD9830	Aged 48 Hrs 220F	81,000 (559)	76,000 (523)	28

Mechanical Properties - Impact

					•		
I	Shielding Medium	Ref. No.	Testing Conditions	Temp. F (C)	Individuals ft.lb.(J)	Avg. ft.lb.(J)	Туре
I	M21-ArC-25	PD9829	As Welded	0 (-18)	125,119,115 (169,161,156)	120 (162)	Charpy-V-Notch
I	M21-ArC-25	PD9829	As Welded	-20 (-29)	95,99,94 (129,134,127)	96 (130)	Charpy-V-Notch
I	C1 (100% CO2)	PD9830	As Welded	0 (-18)	95,88,90 (129,119,122)	91 (123)	Charpy-V-Notch
I	C1 (100% CO2)	PD9830	As Welded	-20 (-29)	28,47,53 (38,64,72)	43 (58)	Charpy-V-Notch

Observational Association										
PD9830 Conforms Horizontal: Overhead: Conforms Vertical: Conforms										
PD9829	Conforms	Horizontal :	Overhead : Conforms	Vertical : Conforms						
Ref.No.	Radiographic Inspection		Fillet Weld Test							

Chemical Analysis

M21-ArC-25 / PD9829	Shielding Medium / Ref. No	С	Mn	P	S	Si	Cu	Cr	V	Ni	Мо	ΑI	Ti	Nb	Со	В ۱	NS	3n I	Fe	Sb	N	Mg	Zn	Be	Sb	As
C1 (100% CO2) / PD9830	M21-ArC-25 / PD9829	0.05	1.48	0.010	0.008	0.38	0.02	0.03	0.02	0.01	0.01															
	C1 (100% CO2) / PD9830	0.04	1.40	0.011	0.008	0.33	0.02	0.03	0.02	0.01	0.01															

Diffusible Hydrogen Collected per AWS A4.3

	M21-ArC-25	5.5 ml/100g of weld metal for 1/16 in diameter 47% relative humidity
IL	C1 100% CO2	4.3 ml/100g of weld metal for 1/16 in diameter 47% relative humidity

Dave Thomas, Quality Assurance Rep.

Certification and Limited Warranty - Data for the above supplied product are those obtained when welded and tested in accordance with the above specification. All tests for the above classification were satisfied. Other tests and procedures may produce different results.