308L Sterling®



AWS A5.4: E308L-17

WELDING POSITIONS:

FEATURES:

BENEFITS:

- Spray arc transfer
- Directional arc
- Easy strike and re-strike
- Limited all-position
- Self-detaching slag

- Low spatter and less clean-up
- Metal goes where directed
- · Easy to use, less chance of starting defects
- Welds extremely well in flat, horizontal, and limited capability in vertical (up) and overhead positions
- · Less chance of slag inclusions

TYPE OF CURRENT: Direct Current Electrode Positive (DCEP) or AC

RECOMMENDED WELDING PROCEDURES:

ARC LENGTH: Short (less than 1/2 the diameter of the electrode)

FLAT & HORIZONTAL: Angle electrode 10-15° from 90°

VERTICAL-UP: Use weaving techniques. Reduced amperage compared to flat position setting

VERTICAL-DOWN: Not recommended

OVERHEAD: Use slight weaving motion within the puddle

STORAGE: Sterling electrodes have a high degree of moisture resistance; however, for critical applications, the electrodes

should be held at 215°F - 300°F after opening.

RECONDITIONING: If exposed to atmosphere for extended periods, recondition at 660°F for 2 hours.

TYPICAL WELD METAL PROPERTIES* (Chem Pad):

Weld Metal Analysis (%)		AWS Spec
Carbon (C)	0.02	0.04 max
Manganese (Mn)	0.70	0.5 to 2.5
Phosphorus (P)	0.020	0.04 max
Sulphur (S)	0.013	0.03 max
Silicon (Si)	0.70	0.90 max
Copper (Cu)	0.10	0.75 max
Chromium (Cr)	20.0	18.0 to 21.0
Nickel (Ni)	9.5	9.0 to 11.0
Molybdenum (Mo)	0.07	0.75 max

TYPICAL MECHANICAL PROPERTIES* (As Welded):

Mechanical Tests		AWS Spec
Tensile Strength	84,000 psi (579 MPa)	80,000 psi
Yield Strength	65,000 psi (448 MPa)	Not required
Elongation % in 2" (50 mm)	39%	35%
DeLong Ferrite Number Range	4-12	Not required
Schaeffler Number Range	4-12	Not required
WRC Number Range (1992)	4-12	Not required

Note: Nitrogen (N) assumed to be 0.06% for calculation purposes.

308L Sterling®

Diameter		Weld		Amperage Range	
Inches	(mm)	Position	Type of Current	Min.	Max.
3/32	(2.5)	Flat & Horizontal	DCEP or AC	35	60
1/8	(3.2)	Flat & Horizontal	DCEP or AC	40	80
5/32	(4.0)	Flat & Horizontal	DCEP or AC	80	120
3/16	(5.0)	Flat & Horizontal	DCEP or AC	150	190

Maintaining a proper welding procedure - including pre-heat and interpass temperatures - may be critical depending on the type and thickness of steel being welded.

AVAILABLE DIAMETERS AND PACKAGES:

Diam Inches	eter (mm)	Len Inches	gth (mm)	5-Lb. Can	6-Lb. Can	7-Lb. Can
3/32	(2.5)	12	(300)	S493931-036	_	_
1/8	(3.2)	14	(350)	_	S493944-032	_
5/32	(4.0)	14	(350)	_	S493951-032	_
3/16	(5.0)	14	(350)	_	_	S493958-039

CONFORMANCES AND APPROVALS:

- AWS A5.4, Class E308L-17
- · ASME SFA 5.4

TECHNICAL QUESTIONS? For technical support of Hobart Filler Metals products, contact the Applications Engineering department by phone toll-free at 1-800-532-2618 or by e-mail at Applications.Engineering@hobartbrothers.com

CAUTION:

Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36th St., Miami, FL 33166 (can also be downloaded online at www.aws.org); OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210

Safety Data Sheets on any Hobart Brothers Company product may be obtained from Hobart Customer Service or at www.hobartbrothers.com.

Because Hobart Brothers Company is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.

Hobart and Sterling are registered trademarks of Hobart Brothers Company, Troy, Ohio.

150-C, INDEX

