FabCO<sup>®</sup> 115K3

AWS A5.29: E110T5-K3 C H4, E110T5-K3M H4



## WELDING POSITIONS:

Features:	Benefits:	$\bigcirc \bigcirc \bigcirc \bigcirc$
<ul> <li>Basic slag system</li> <li>"H4" low-hydrogen weld deposit</li> <li>Excellent arc drive/dig</li> <li>High-strength weld deposit</li> <li>Large-diameter availability, optimized for welding in the flat &amp; horizontal positions</li> </ul>	<ul> <li>Provides consistently excellent mechanic help ensure weld integrity in critical appli</li> <li>Helps minimize the risk of hydrogen-indu</li> <li>Assists producing welds with consistent is quality along the entire weld joint</li> <li>Suitable for many 110+ KSI (730+ MPa) low-alloy (HSLA) and quench &amp; tempere</li> <li>Allows the use of high currents and wire help improve weldability and increase pro-</li> </ul>	cal properties to cations iced cracking fusion and overall high-strength d (Q&T) steels feed speeds to oductivity
APPLICATIONS: • Single or multi-pass welding • Pressure vessels • 110+ KSI (760 MPa) HSI A and O&T steels	Structural fabrication     ASTM A514 [<2-1/2" (63mm)]	eavy equipment ffshore

• 110+ KSI (760 MPa) HSLA and Q&T steels

**SLAG SYSTEM:** Slow-freezing, basic-type, flux-cored wire

**SHIELDING GAS:** 100% Carbon Dioxide (CO<sub>2</sub>), 75% Argon (Ar)/25% Carbon Dioxide (CO<sub>2</sub>) 35-50 cfh, (17-24 l/min) **TYPE OF CURRENT:** Direct Current Electrode Positive (DCEP)

**STANDARD DIAMETERS:** 1/16" (1.6 mm), 3/32" (2.4 mm)

**RE-DRYING:** Not recommended

STORAGE: Product should be stored in a dry, enclosed environment, and in its original intact packaging

#### **TYPICAL WELD METAL CHEMISTRY\* (Chem Pad):**

Weld Metal Analysis (%)	100% CO <sub>2</sub>	75% Ar/25% CO <sub>2</sub>	AWS Spec
Carbon (C)	0.04	0.05	0.15
Manganese (Mn)	1.64	1.76	0.75-2.25
Silicon (Si)	0.40	0.43	0.80
Phosphorus (P)	0.008	0.007	0.030
Sulphur (S)	0.007	0.007	0.030
Nickel (Ni)	2.08	2.15	1.25-2.60
Molybdenum (Mo)	0.37	0.34	0.25-0.65

Note: AWS specification single values are maximums.

## TYPICAL DIFFUSIBLE HYDROGEN\*:

Hydrogen Equipment	100% CO <sub>2</sub>	75% Ar/25% CO <sub>2</sub>	AWS Spec
(Gas Chromatography)	2.0 ml/100g	2.5 ml/100g	4.0 ml/100g Maximum

# **TYPICAL MECHANICAL PROPERTIES\* (As Welded):**

Mechanical Tests	100% CO₂	75% Ar/25% CO <sub>2</sub>	AWS Spec
Tensile Strength	117,000 psi (807 MPa)	122,000 psi (841 MPa)	110,000-130,000 psi (760-900 MPa)
Yield Strength	105,000 psi (724 MPa)	106,000 psi (731 MPa)	98,000 psi (680 MPa) Minimum
Elongation % in 2" (50 mm)	20%	20%	15% Minimum

# **TYPICAL CHARPY V-NOTCH IMPACT VALUES\* (As Welded):**

CVN Temperatures	100% CO <sub>2</sub>	75% Ar/25% CO₂	AWS Spec
CVN @-60°F (-50°C)	58 ft•lbs (79 Joules)	54 ft•lbs (73 Joules)	20 ft•lbs (27 Joules) Minimum

\*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers Company expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the AWS A5.29 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers Company.

Hobart Brothers Company • 101 Trade Square East • Troy, OH 45373 PH: (800) 424-1543 • FX: 800-541-6607 • www.hobartbrothers.com

# FabCO<sup>®</sup> 115K3

Diam Inches	eter (mm)	Weld Position	Amps	Volts	Wire Sp in/min	e-Feed beed (m/min)	Depo R Ibs/hr	osition ate (kg/hr)	Contact Work Dis Inches	Tip to stance (mm)
1/16	(1.6)	Flat & Horizontal	200	25	200	(5.1)	7.1	(3.2)	3/4	(19)
1/16	(1.6)	Flat & Horizontal	350	28	360	(9.1)	13.2	(6.0)	3/4	(19)
1/16	(1.6)	Flat & Horizontal	425	34	485	(12.3)	18.0	(8.2)	1	(25)
3/32	(2.4)	Flat & Horizontal	300	26	130	(3.3)	10.2	(4.6)	1	(25)
3/32	(2.4)	Flat & Horizontal	450	31	215	(5.5)	17.2	(7.8)	1	(25)
3/32	(2.4)	Flat & Horizontal	600	35	340	(8.6)	27.4	(12.4)	1 1/4	(32)

 Maintaining a proper welding procedure - including pre-heat and interpass temperatures - may be critical depending on the type and thickness of steel being welded.

• See Above: This information was determined by welding using 100% CO<sub>2</sub> shielding gas with a flow rate between 35-50 cfh (17-24 l/min). When using 75% Argon (Ar)/25% CO<sub>2</sub> shielding gas, reduce voltage by approximately one volt.

**STANDARD DIAMETERS AND PACKAGES:** For a complete list of diameters and packaging, please contact Hobart Brothers at (800) 424-1543 or (937) 332-5188 for International Customer Service.

Diameter Inches (mm)		60-lb. (27.2kg) Coil
1/16	(1.6)	S651519-002
3/32	(2.4)	S651529-002

**CONFORMANCES AND APPROVALS:** 

- AWS A5.29, E110T5-K3C H4, E110T5-K3M H4
- AWS A5.29M, E760T5-K3C H4, E760T5-K3M H4
- ASME SFA 5.29, E110T5-K3C H4, E110T5-K3M H4
- ABS, 100% CO2, E110T5-K3C H4

**TECHNICAL QUESTIONS?** For technical support of Hobart Filler Metals products, contact the Applications Engineering department by phone toll-free at 1-800-532-2618 or by e-mail at <u>Applications.Engineering@hobartbrothers.com</u>

#### CAUTION:

Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 St, # 130, Doral, FL 33166-6672 (can also be downloaded online at www.aws.org); OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210

Material Safety Data Sheets on any Hobart Brothers Company product may be obtained from Hobart Customer Service or at www.hobartbrothers.com. Because Hobart Brothers Company is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.

Hobart and FabCO are registered trademarks of Hobart Brothers Company, Troy, Ohio.



