



## Certificate of Conformance to Requirements for Welding Electrode

**Product Type:** SubCOR EM13KS MOD  
**Classification:** EC1  
**Specifications:** AWS A5.17/A5.17M; ASME SFA 5.17  
**Diameter Tested:** 5/32"  
**Date Tested:** 7/11/2025  
**Date Generated:** 7/18/2025

This is to certify that the product named above and supplied on the referenced order number is of the same classification, manufacturing process, and material requirements as the material which was used for the test that was concluded on the date shown, the results of which are shown below. All tests required by the specifications shown for classification were performed at that time and the material tested met all requirements. It was manufactured and supplied by the Quality System Program of Hobart Brothers, which meets the requirements of ISO 9001, ANSI/AWS A5.01, and other specification and Military requirements, as applicable. This document supplies actual test results of non-specific inspection in conformance with the requirements of EN 10204, type 2.2 certification.

**THE STEEL USED IN THIS LOT OF MATERIAL WAS MELTED AND MANUFACTURED IN THE U.S.A.**

**Test Settings**

| Shielding Medium     | Amps / Polarity | Volts | WFS<br>in/min(m/min) | ESO in(mm) | Preheat F(C) | Interpass F(C) | Travel Speed<br>in/min(cm/min) |
|----------------------|-----------------|-------|----------------------|------------|--------------|----------------|--------------------------------|
| HA-495 (F7A2-EC1)    | 525 / DCEP      | 28    | 70 (1.8)             | 1.25 (32)  | Room Temp    | 300(149)       | 17 (43.2)                      |
| SWX 150 (F7A8-EC1)   | 525 / DCEP      | 29    | 67 (1.7)             | 1.25 (32)  | Room Temp    | 300(149)       | 16 (40.6)                      |
| SWX 150 (F7P8-EC1)   | 525 / DCEP      | 29    | 63 (1.6)             | 1.25 (32)  | Room Temp    | 300(149)       | 16 (40.6)                      |
| SWX 120 (F7A8-EC1)   | 525 / DCEP      | 29    | 64 (1.6)             | 1.25 (32)  | Room Temp    | 300(149)       | 16 (40.6)                      |
| SWX 120 (F7P8-EC1)   | 525 / DCEP      | 29    | 64 (1.6)             | 1.25 (32)  | Room Temp    | 300(149)       | 16 (40.6)                      |
| HN-590 (F7A8-EC1 H8) | 525 / DCEP      | 29    | 65 (1.7)             | 1 1/4 (32) | Room Temp    | 300(149)       | 16 (40.6)                      |
| HN-590 (F7A8-EC1 H8) | 525 / DCEP      | 29    | 65 (1.7)             | 1 1/4 (32) | Room Temp    | 300(149)       | 16 (40.6)                      |

**Mechanical Properties - Tensile**

| Shielding Medium     | Ref. No. | Testing Conditions | Ult. Tensile Strength psi (MPa) | Yield Strength psi (MPa) | Elong.% in 2" |
|----------------------|----------|--------------------|---------------------------------|--------------------------|---------------|
| SWX 150 (F7A8-EC1)   | PE7290   | Aged 48 Hrs 220F   | 82,000 ( 563 )                  | 70,000 ( 485 )           | 29            |
| SWX 150 (F7P8-EC1)   | PE7305   | SR 1 Hr @ 1150F    | 74,000 ( 511 )                  | 59,000 ( 407 )           | 31            |
| SWX 120 (F7A8-EC1)   | PE7306   | Aged 48 Hrs 220F   | 81,000 ( 556 )                  | 71,000 ( 488 )           | 28            |
| SWX 120 (F7P8-EC1)   | PE7307   | SR 1 Hr @ 1150F    | 79,000 ( 546 )                  | 66,000 ( 456 )           | 28            |
| HA-495 (F7A2-EC1)    | PE6369   | Aged 48 Hrs 220F   | 89,000 ( 612 )                  | 79,000 ( 544 )           | 27            |
| HN-590 (F7A8-EC1 H8) | PE9624   | Aged 48 Hrs 220F   | 84,000 ( 577 )                  | 71,000 ( 487 )           | 27            |
| HN-590 (F7A8-EC1 H8) | PE9625   | SR 1 Hr @ 1050F    | 80,000 ( 552 )                  | 64,000 ( 441 )           | 30            |

**Mechanical Properties - Impact**

| Shielding Medium     | Ref. No. | Testing Conditions | Temp. F (C) | Individuals ft.lb.(J)  | Avg. ft.lb.(J) | Type           |
|----------------------|----------|--------------------|-------------|------------------------|----------------|----------------|
| HA-495 (F7A2-EC1)    | PE6369   | As Welded          | -40 (-40)   | 51,54,74 (69,73,100)   | 60 ( 81 )      | Charpy-V-Notch |
| SWX 150 (F7A8-EC1)   | PE7290   | As Welded          | -80 (-62)   | 17,73,97 (23,99,132)   | 62 ( 85 )      | Charpy-V-Notch |
| SWX 150 (F7P8-EC1)   | PE7305   | SR 1 Hr @ 1150F    | -80 (-62)   | 99,92,95 (134,125,129) | 95 ( 129 )     | Charpy-V-Notch |
| SWX 120 (F7A8-EC1)   | PE7306   | As Welded          | -80 (-62)   | 46,68,90 (62,92,122)   | 68 ( 92 )      | Charpy-V-Notch |
| SWX 120 (F7P8-EC1)   | PE7307   | SR 1 Hr @ 1150F    | -80 (-62)   | 23,58,38 (31,79,52)    | 40 ( 54 )      | Charpy-V-Notch |
| HN-590 (F7A8-EC1 H8) | PE9624   | As Welded          | -80 (-62)   | 30,24,35 (41,33,47)    | 30 ( 40 )      | Charpy-V-Notch |
| HN-590 (F7A8-EC1 H8) | PE9625   | SR 1 Hr @ 1150F    | -80 (-62)   | 30,37,56 (41,50,76)    | 41 ( 56 )      | Charpy-V-Notch |

| Ref.No. | Radiographic Inspection | Fillet Weld Test |            |            |
|---------|-------------------------|------------------|------------|------------|
| PE7290  | Conforms                | Horizontal :     | Overhead : | Vertical : |
| PE7305  | Conforms                | Horizontal :     | Overhead : | Vertical : |
| PE7306  | Conforms                | Horizontal :     | Overhead : | Vertical : |
| PE7307  | Conforms                | Horizontal :     | Overhead : | Vertical : |
| PE6369  | Conforms                | Horizontal :     | Overhead : | Vertical : |
| PE9624  | Conforms                | Horizontal :     | Overhead : | Vertical : |
| PE9625  | Conforms                | Horizontal :     | Overhead : | Vertical : |

**Chemical Analysis**

| Shielding Medium / Ref. No     | C    | Mn   | P     | S     | Si   | Cu   | Cr | V | Ni | Mo   | Al | Ti | Nb | Co | B | W | Sn | Fe | Sb | N | Mg | Zn | Be | Sb | As |
|--------------------------------|------|------|-------|-------|------|------|----|---|----|------|----|----|----|----|---|---|----|----|----|---|----|----|----|----|----|
| HN-590 (F7A8-EC1 H8) / CF17021 | 0.06 | 1.73 | 0.018 | 0.011 | 0.38 | 0.07 |    |   |    | 0.08 |    |    |    |    |   |   |    |    |    |   |    |    |    |    |    |
| HA-495 (F7A2-EC1) / PE6369     | 0.07 | 1.62 | 0.024 | 0.010 | 0.73 | 0.05 |    |   |    | 0.09 |    |    |    |    |   |   |    |    |    |   |    |    |    |    |    |
| SWX 150 (F7A8-EC1) / PE7290    | 0.09 | 0.98 | 0.012 | 0.006 | 0.38 | 0.05 |    |   |    | 0.09 |    |    |    |    |   |   |    |    |    |   |    |    |    |    |    |
| SWX 120 (F7A8-EC1) / PE7306    | 0.07 | 1.51 | 0.019 | 0.010 | 0.31 | 0.07 |    |   |    | 0.08 |    |    |    |    |   |   |    |    |    |   |    |    |    |    |    |

**Diffusible Hydrogen Collected per AWS A4.3**

|                      |  |
|----------------------|--|
| SWX 150(F7A8-EC1-H8) | 5.6 ml/100g of weld metal for 5/32 in diameter 42% relative humidity |
| SWX 120(F7A8-EC1-H8) | 7.2 ml/100g of weld metal for 5/32 in diameter 40% relative humidity |
| HN-590 (F7A8-EC1 H8) | 2.9 ml/100g of weld metal for 5/32 in diameter 21% relative humidity |

*James A. Owens*

James A. Owens, Q.A. Specialist

Certification and Limited Warranty - Data for the above supplied product are those obtained when welded and tested in accordance with the above specification. All tests for the above classification were satisfied. Other tests and procedures may produce different results.