FabCO® 81K2-C



AWS A5.29: E81T1-K2CJ H8

WELDING POSITIONS:



FEATURES:

BENEFITS:

- · Fast freezing slag
- · Excellent impact toughness
- · Low diffusible hydrogen
- · Low spatter levels
- Smooth, stable arc characteristics
- Suitable for welding out of position
- · Resists cracking in severe applications
- · Minimizes risk of hydrogen-induced cracking
- Reduces clean-up time, improves productivity
- Improves operator appeal

APPLICATIONS:

- Single or multi-pass welding
- General fabrication
- · Shipbuilding
- High-strength low-alloy steels
 Offshore
- · Heavy equipment

SLAG SYSTEM OR WIRE TYPE: Fast freezing, rutile type, flux-cored wire **SHIELDING GAS:** 100% Carbon Dioxide (CO₂), 35-50 cfh (14-24 l/min)

TYPE OF CURRENT: Direct Current Electrode Positive (DCEP) STANDARD DIAMETERS: 0.045" (1.2 mm), 1/16" (1.6 mm)

RE-DRYING: Not recommended

STORAGE: Product should be stored in a dry, enclosed environment, and in its original intact packaging

TYPICAL WELD METAL CHEMISTRY* (Chem Pad):

Weld Metal Analysis (%)	100% CO ₂	AWS Spec
Carbon (C)	0.04	0.15
Manganese (Mn)	1.05	0.50-1.75
Phosphorus (P)	0.01	0.030
Sulphur (S)	0.008	0.030
Silicon (Si)	0.30	0.80
Nickel (Ni)	1.70	1.00-2.00
Chrome (Cr)	0.025	0.15
Molybdenum (Mo)	0.007	0.35
Vanadium (Va)	0.02	0.05

Note: AWS specification single values are maximums.

TYPICAL DIFFUSIBLE HYDROGEN*:

Hydrogen Equipment	100% CO ₂	AWS Spec
(GAS CHROMATOGRAPHY)	4.2 ml/100g	8.0 ml/100g Maximum

TYPICAL MECHANICAL PROPERTIES* (As Welded):

Mechanical Tests	100% CO ₂	AWS Spec
Tensile Strength	85,000 psi (586 MPa)	80,000-100,000 psi (550-690 MPa)
Yield Strength	80,000 psi (552 MPa)	68,000 psi (470 MPa) Minimum
Elongation % in 2" (50 mm)	23%	19%

TYPICAL CHARPY V-NOTCH IMPACT VALUES* (As Welded):

CVN Temperatures	100% CO ₂	AWS Spec
Avg. at -20°F (-29°C)	85 ft•lbs (115 Joules)	20 ft•lbs (27 Joules) Minimum
Avg. at -40°F (-40°C)	70 ft•lbs (95 Joules)	20 ft•lbs (27 Joules) Minimum "J" Requirement

^{*}The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers LLC expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the AWS A5.29 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers LLC.

FabCO® 81K2-C

Dian	neter	Weld		Wire-Feed Deposition Speed Rate					Contact Tip to Work Distance	
Inches	(mm)	Position	Amps	Volts	in/min	(m/min)	lbs/hr	(kg/hr)	Inches	(mm)
0.045	(1.2)	All Position	150	19-24	250	(6.4)	5.0	(2.3)	3/4	(19)
0.045	(1.2)	All Position	200	20-25	315	(8.0)	6.3	(2.9)	3/4	(19)
0.045	(1.2)	All Position	225	21-26	415	(10.5)	8.2	(3.7)	1	(25)
0.045	(1.2)	Flat & Horizontal	265	23-28	500	(12.7)	9.7	(4.4)	1	(25)
0.045	(1.2)	Flat & Horizontal	275	24-29	530	(13.5)	10.1	(4.6)	1	(25)
0.045	(1.2)	Flat & Horizontal	300	26-31	605	(15.4)	12.1	(5.5)	1	(25)
1/16	(1.6)	All Position	175	19-24	130	(3.3)	3.9	(1.8)	3/4	(19)
1/16	(1.6)	All Position	225	20-25	150	(3.8)	6.3	(2.9)	3/4	(19)
1/16	(1.6)	All Position	275	22-27	235	(6.0)	9.6	(4.4)	1	(25)
1/16	(1.6)	Flat & Horizontal	350	25-30	335	(8.5)	13.6	(6.2)	1	(25)
1/16	(1.6)	Flat & Horizontal	400	27-32	420	(10.7)	17.0	(7.7)	1	(25)

- Maintaining a proper welding procedure including pre-heat and interpass temperatures may be critical depending on the type and thickness of steel being welded.
- All position includes the following: Flat, Horizontal, Vertical Up, and Overhead.
- See Above: This information was determined by welding using 100% Carbon Dioxide (CO₂) shielding gas with a flow rate between 35-50 cfh (14-24 l/min).

DIAMETERS AND PACKAGES: Hobart Brothers periodically evaluates our diameter and package offering based on end user demand. For current package and diameter availability please refer to www.hobartbrothers.com or call Hobart Brothers Customer Service: USA - (800) 424-1543, International - (937) 332-5188.

Diameter Inches (mm)		33-lb. (15kg) Spool	33-lb. (15kg) Vacuum Packed Spool
0.045	(1.2)	_	S288112-053
1/16	(1.6)	S288119-029	_

CONFORMANCES AND APPROVALS:

- AWS A5.29, E81T1-K2CJ H8
- AWS A5.29M, E551T1-K2CJ H8
- ABS, 3Y SA H10 (0.045" diameter)

TECHNICAL QUESTIONS? For technical support of Hobart Filler Metals products, contact the Applications Engineering department by phone toll-free at 1-800-532-2618 or by e-mail at Applications.Engineering@hobartbrothers.com

CAUTION

Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36th St., Miami, FL 33166 (can also be downloaded online at www.aws.org); OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210

Safety Data Sheets on any Hobart Brothers LLC product may be obtained from Hobart Customer Service or at www.hobartbrothers.com.

Because Hobart Brothers LLC is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.

FabCO is a registered trademark of Hobart Brothers LLC, Troy, Ohio.

Revision Date: 190118 (Replaces 170920)

