# Hobart<sup>®</sup> 447A

#### AWS E6013 (E4313\*)



#### WELDING POSITIONS:

FEATURES:	BEN	IEFITS:	
<ul> <li>Excellent arc stability</li> <li>Fast-freeze</li> <li>All position</li> <li>Slag removes easily</li> </ul>	• Exce • Web	ding accuracy and efficie ellent for poor fit-up ds in flat, horizontal, vert ck clean-up	ency ical and overhead positions
<ul><li>APPLICATIONS:</li><li>General fabrication</li></ul>	<ul> <li>Machine parts</li> </ul>	<ul> <li>Metal buildings</li> </ul>	Shaft build-up

TYPE OF CURRENT: AC, Direct Current Electrode Positive (DCEP), or Direct Current Electrode Negative (DCEN)

ARC LENGTH: Average length (1/8" to 1/4")

FLAT: Angle electrodes 10-15° from 90° with higher heat than E6011 electrodes

VERTICAL-UP: Reduce amperage from flat position

VERTICAL-DOWN: Use higher amperage and faster travel, staying ahead of puddle

**OVERHEAD:** Use slight whipping motion; multi-pass for build-up

**STORAGE:** 60° to 100°F, (20° to 40°C) and below 50% relative humidity or holding oven @ 100° to 120°F (38° to 49°C) **RECONDITIONING:** 250° to 300°F, (121° to 149°C) for one hour @ temperature

## TYPICAL WELD METAL CHEMISTRY\* (Chem Pad):

Weld Metal Analysis (%)		AWS Spec (max)
Carbon (C)	0.08	0.20
Manganese (Mn)	0.39	1.20
Phosphorus (P)	0.012	Not required
Sulphur (S)	0.016	Not required
Silicon (Si)	0.25	1.00
Nickel (Ni)	0.04	0.30
Chromium (Cr)	0.04	0.20
Molybdenum (Mo)	0.01	0.30
Vanadium (V)	0.01	0.08

Note: AWS specification single values are maximums.

#### **TYPICAL MECHANICAL PROPERTIES\* (As Welded):**

Mechanical Tests		AWS Spec (min)
Tensile Strength	74,000 psi (514 MPa)	60,000 psi (414 MPa)
Yield Strength	67,000 psi (463 MPa)	48,000 psi (331 MPa)
Elongation % in 2" (50 mm)	30%	17%
Reduction of Area	25% to 55%	Not required

TYPICAL CHARPY V-NOTCH IMPACT VALUES\* (As Welded): Not applicable

<sup>\*</sup>The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers LLC expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the AWS A5.1 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers LLC.

# Hobart<sup>®</sup> 447A

Diameter Inches (mm)		Type of Current	Minimum Amps	Optimum Amps	Maximum Amps
3/32	(2.4)	AC, DCEN or DCEP	40	70	80
1/8	(3.2)	AC, DCEN or DCEP	70	100	120
5/32	(4.0)	AC, DCEN or DCEP	130	150	160
3/16	(4.8)	AC, DCEN or DCEP	140	190	220

\*For out-of-position welding, reduce amperage shown by 15%.

Diam Inches	eter (mm)	Type of Current	Amps	Volts		sition ate (kg/hr)	Deposition Efficiency %
3/32	(2.4)	AC, DCEN or DCEP	70	19-24	1.35	(0.6)	63.7
1/8	(3.2)	AC, DCEN or DCEP	100	18.5-22.5	1.85	(0.8)	66.1
5/32	(4.0)	AC, DCEN or DCEP	150	20-24	2.67	(1.2)	61.6
3/16	(4.8)	AC, DCEN or DCEP	190	20-22.5	4.22	(1.9)	62.7

• Maintaining a proper welding procedure - including pre-heat and interpass temperatures - may be critical depending on the type and thickness of steel being welded.

**STANDARD DIAMETERS AND PACKAGES:** For a complete list of diameters and packaging, please contact Hobart Brothers at (800) 424-1543 or (937) 332-5188 for International Customer Service.

Dian Inches	neter (mm)	5-lb. (2.3kg) Plastic Pak	10-lb. (4.5kg) Plastic Pak	50-lb. (22.7kg) Carton
Net Palle	et Weight	2000-lb. (904 kg)	2100-lb. (951 kg)	3000-lb. (1361 kg)
3/32	(2.4)	S113832-045	S113832-089	S113832-031
1/8	(3.2)	S113844-045	S113844-089	S113844-031
5/32	(4.0)	—	S113851-089	S113851-031
3/16	(4.8)	—	—	S113858-031

## CONFORMANCES AND APPROVALS:

- AWS A5.1, E6013
- ASME SFA 5.1, F-2, A-1
- ABS, E6013
- CWB, E4313

**TECHNICAL QUESTIONS?** For technical support of Hobart Filler Metals products, contact the Applications Engineering department by phone toll-free at 1-800-532-2618 or by e-mail at <u>Applications.Engineering@hobartbrothers.com</u>

#### CAUTION:

Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36th St., Miami, FL 33166 (can also be downloaded online at www.aws.org); OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210

Data Sheets on any Hobart Brothers LLC product may be obtained from Hobart Customer Service or at www.hobartbrothers.com. Because Hobart Brothers LLC is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.



Hobart is a registered trademark of Hobart Brothers LLC, Troy, Ohio.

Revision Date: 201105 (Replaces 171031) 612-E, INDEX